



TECHNICAL DATASHEET

Code : FOR.QUA.06
Version : 00
Date of application : 01-11-2018

HERMAID PA6 1001

Product Description: Polyamide (PA6), Unfilled, lubricated

Properties	Condition	Min/Max	Units	Standards
Physical properties				
Density	23°C	1.12-1.14	g/cm ³	ISO1183
Melt –Flow-Index			-	ISO1133
Humidity	110°C	0.1-0.2	%	ISO15512
Ash Content	625°C	28-32	%	ISO 1172
Mechanical properties				
Tensile modulus	50mm/min	-	MPa	ISO 527-2
Tensile stress at break	5mm/min	75-80	MPa	ISO 527-2
Elongation at break	5mm/min	40-45	%	ISO 527-2
Flexural modulus	2mm/min	2900-2950	MPa	ISO 178
Flexural strength	5mm/min	110-120	MPa	ISO 178
Izod impact strength	5J	-	Kj/m ²	ISO180
Izod notched impact strength	5J	8.5	Kj/m ²	ISO180
Charpy impact strength	5.5J	-	Kj/m ²	ISO179/1eU
Charpy notched impact strength	5.5J	-	Kj/m ²	ISO179/1eA
Thermal properties				
Melting and crystallization temperature	10°C/min	220-222	°C	ISO11357-3
HDT /A Heat deflection temperature	1.8MPa	-	°C	ISO 75/1-2
HDT/B Heat deflection temperature	0.45MPa	-	°C	ISO 75/1-2
Vicat : Softening point of materials	-		°C	ISO 306
Electrical properties				
Surface resistivity	-	1.00e+13	Ohm-cm	IEC 60093
Volume resistivity	-	1.00e+15	Ohm-cm	IEC 60093
Flammability				
Flammability	HB		CLASS	UL94

The information contained herein is based on our current knowledge and experience. A legally binding promise of certain characteristics or suitability for a concrete individual case cannot be derived from this information. The information here is not intended to release processors and users from the responsibility of carrying out their own tests and inspections in each concrete individual case.



TECHNICAL DATASHEET

Code : FOR.QUA.06
Version : 00
Date of application : 01-11-2018

Characteristics

- *Delivery from
Pellets, natural color
- *Chemical resistance
General chemical resistance
- *Applications : extrusion, injection molding
Automotive, electrical and electronic, general purpose.

Processing Properties :

Feed Temperature	225-230°C	Compression zone
Middle Barrel Temperature	230-240°C	
Front Barrel Temperature	240-250°C	
Nozzle Temperature	241-260°C	
Melt Temperature	230-260°C	
Mold Temperature	80.0 -100 °C	

Packaging & delivery

PE aluminum bag : 25kg/bag (pallet 1000kg)
Note to avoid moisture, insulation and breakage in transportation
Delivery detail : 30 days

Contact :

Hermess Compounds _ Rue De Nabeul ZI M'Ghira 3 _ Ben Arous Tunisie
E-mail : resp.laboratoire@gmail.com
Tél : +216 58 597 174 / +216 36 404 520 Fax : +216 36 404 523